


# Gaskamine240

1,3-benzenedimethanamine, reaction products with styrene

CAS: 404362-22-7

EINECS: 445-790-1



## Product Information

### Features

Good chemical resistance, Low viscosity and long pot life  
Ready to use (no modification needed)

### Application

Epoxy resin curing agent (Flooring, Protective coating)

### Physical Properties

Appearance, (Visual) \_\_\_\_\_ Colorless liquid  
Color, (Gardner) \_\_\_\_\_ 1 - 2  
Flash point, °C (Cleveland open tester) \_\_\_\_\_ 212  
Viscosity, mPa·s, 25°C \_\_\_\_\_ 66  
Specific gravity, 20°C \_\_\_\_\_ 1.049  
Amine value, mgKOH/g \_\_\_\_\_ 403  
Theoretical Active Hydrogen Equivalent Weight \_\_\_\_\_ 103  
Solubility \_\_\_\_\_ Soluble in methanol, xylene,  
toluene, acetone  
Insoluble in water

### Specification

Appearance, (Visual) \_\_\_\_\_ Colorless liquid  
Color, (Gardner) \_\_\_\_\_ < 3  
Viscosity, mPa·s, 25°C \_\_\_\_\_ 50 - 85  
Total amine value \_\_\_\_\_ 390 - 415  
Moisture, % \_\_\_\_\_ < 0.2

### Container Information

Available in 200 kg steel drums.

### Safety & Handling

Avoid breathing vapor and direct contact with skin, eyes and clothing.  
Always refer to the MSDS for detailed safety information.

### Contact Information

Email : [mxda@mgc.co.jp](mailto:mxda@mgc.co.jp)

Website : [www.mgc.co.jp](http://www.mgc.co.jp)